

Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 326452

Report Information

Submitting Organisation : 00109358 : Parchem Construction Supplies Pty Ltd

Account: 130335: Parchem Construction Supplies Pty Ltd

AWQC Reference: 130335-2021-CSR-6 : Prod Test: Fosroc Renderoc HB70 Plus

Project Reference: PT-4758

Product Designation: Fosroc Renderoc HB70 Plus

Composition of Product : Portland Cement.

Product Manufacturer: Parchem Construction Supplies, Wyong, NSW, AUSTRALIA.

Use of Product : In-Line/Concrete Repair Mortar.

Sample Selection: As provided by the submitting organisation.

Testing Requested: AS/NZS 4020 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING

WATER

Product Type : Composite

Samples: Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2018

Extracts: Extracts were prepared as described in Appendix/Clause C, D, E, F, G, H, 6.8.

Project Completion Date: 06-Dec-2021

Project Comment: Product sample received on the 16-Aug-2021 and testing commenced 20-Sep-2021.

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL

THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER

M Marion

Michael Glasson APPROVED SIGNATORY





250 Victoria Square Tel: 1300 653 366 Adelaide SA 5000 Fax: 1300 883 171

Email: producttesting@awqc.com.au



Internet: www.awqc.com.au

FINAL REPORT

Report ID: 326452

Summary of Results

APPENDIX/CLAUSE	RESULTS
C - Taste	Passed at an exposure of 15000 mm² per Litre.
D - Appearance	Passed at an exposure of 15000 mm² per Litre.
E - Growth of Aquatic Micro-organisms	Passed at an exposure of 15000 mm² per Litre.
F — Cytotoxic Activity	Passed at an exposure of 15000 mm² per Litre.
G - Mutagenic Activity	Passed at an exposure of 15000 mm² per Litre.
H - Metals	Passed at an exposure of 15000 mm² per Litre.
6.8 — Organic Compounds	Passed at an exposure of 15000 mm² per Litre.

Test Methods

Test(s) in Appendix	AWQC Test Method	Reference Method
С	T0320-01	AS/NZS 4020:2018
D	TO029-01 & TO018-01	APHA 2120c & APHA 2130b
E	TO014-03	APHA 4500 O G
F	TM-001	AS/NZS 4020:2018
G	TM-002	AS/NZS 4020:2018
Н	TIC-006	EPA 200.8

Organic Test Methods

Test(s) in Clause	Test Method	Reference Method
Clause 6.8	TMZ-M36	USEPA524.2
	EP239	USEPA521
	EP132-LL	USEPA_SW846-8270D
	EP075C	USEPA_SW846-8270D
	EP075ASIM	USEPA_SW846-8270D

Summary Comment:

The compound was applied (to glass slides) and cured for 7 days at 20°C prior to testing (ratio of 500g to 72.5mL of drinking water). Thirteen sequential soakings were performed to obtain a pH < 9.0. In accordance with section A8 (Cementitious Products).







Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 326452

CLAUSE 6.2 Taste

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75

mm x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts

were prepared using 1000 mL volumes of pre-conditoning water(Al 12.6).

Extraction Temperature 20°C ± 2°C.

Test Method Taste (Appendix C)

Test Information

Scaling Factor Not applicable.

Results Not detected (sample and controls).

Evaluation The product passed the requirements of clause 6.2 when tested at an exposure of 15000 mm

² per Litre.

Number of Samples 2.

Test Comment The 24 hour extracts were not analysed in this test.

Peter Christopoulos
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



Email: producttesting@awgc.com.au

AWQC

Internet: www.awqc.com.au

FINAL REPORT

Report ID: 326452

CLAUSE 6.3 Appearance

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75

mm x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts

were prepared using 1000 mL volumes of pre-conditoning water(Al 12.6).

Extraction Temperature $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

Test Method Appearance (Appendix D)

Scaling Factor Not applicable.

Results

	Test (- Blank)	Maximum Allowed	<u>Units</u>
Colour	<1	5	HU
Turbidity	<0.1	0.5	NTU

Evaluation The product passed the requirements of clause 6.3 when tested at an exposure of 15000 mm

² per Litre.

Number of Samples 1.

Test Comment Not applicable.

Andrew Paul Ford

APPROVED SIGNATORY





AWQC

Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 326452

CLAUSE 6.4 Growth of Aquatic Micro-organisms

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75

mm x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts

were prepared using 1000 mL volumes of test water.

Test Method Growth of Aquatic Micro-organisms (Appendix E)

Inoculum The volume of the inoculum was 100 mL

Scaling Factor Not applicable.

Results

Mean Dissolved Oxygen Control 7.7 mg/L

Mean Dissolved Oxygen Difference Positive Reference 5.3 mg/L

Negative Reference 0.1 mg/L

Test 0.20 mg/L

Evaluation The product passed the requirements of clause 6.4 when tested at an exposure of 15000 mm

² per Litre.

Number of Samples 1.

Test Comment Not applicable.

Thuy Diep
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

Elwa



Email: producttesting@awqc.com.au



Internet: www.awqc.com.au

FINAL REPORT

Report ID: 326452

CLAUSE 6.5 Cytotoxic Activity

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75

mm x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts

were prepared using 1000 mL volumes of pre-conditoning water(Al 12.6).

Extraction Temperature $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

Test Method Cytotoxic Activity (Appendix F)

Scaling Factor Not applicable.

Results Non-Cytotoxic (sample and controls).

Evaluation The product passed the requirements of clause 6.5 when tested at an exposure of 15000 mm

² per Litre.

Number of Samples 1.

subsequently used to grow a cell line (ATCC Number CCL 81) in the analysis. In addition

zinc sulphate (0.4 mmol) was used for the positive control in the analysis.



Mira Maric

APPROVED SIGNATORY





AWQC

Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 326452

CLAUSE 6.6 Mutagenic Activity

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75

mm x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts

were prepared using 1000 mL volumes of pre-conditoning water(Al 12.6).

Extraction Temperature 20°C ± 2°C.

Test Method Mutagenic Activity (Appendix G)

Scaling Factor Not applicable.

Results

Bacteria Strain Number of Revertants per Plate

Salmonella typhimurium TA98 Mean ± Standard deviation	S9 -	Blank 25, 30, 15 23.3 ± 7.6	Sample Extract 23, 22, 27 24.0 ± 2.6	Positive Controls 3021, 3241, 3525 3262.3 ± 252.7	<u>NPD (</u> 20μg)
Mean ± Standard deviation	+	28, 25, 31 28.0 ± 3.0	21, 29, 19 23.0 ± 5.3	2908, 2825, 3312 3015.0 ± 260.5	<u>2-AF (</u> 20μg)
Salmonella typhimurium TA102 Mean ± Standard deviation	-	243, 288, 321 284.0 ± 39.2	234, 271, 277 260.7 ± 23.3	1121, 2736, 1397 1751.3 ± 863.8	<u>Mitomycin C(</u> 10μg)
Mean ± Standard deviation	+	336, 283, 267 295.3 ± 36.1	311, 384, 341 345.3 ± 36.7	1700, 1435, 1369 1501.3 ± 175.2	

Comments S9 was used as the metabolic activator. NPD (4-nitro-o-phenylenediamine) and Mitomycin

C are specific positive controls for strains TA98 - and TA102 (- and +) respectively, while 2-AF (2-aminofluorene) when used in conjunction with S9 is a positive control for TA98+.

Evaluation The product passed the requirements of clause 6.6 when tested at an exposure of 15000 mm

² per Litre.

Number of Samples 1.

Test CommentThe differences in the mean number of revertants between the blank and test extracts do not

exceed two standard deviations; accordingly there is no evidence of a mutagenic response.

Peter Christopoulos
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



ABN 69336525019

Page 7 of 12

Email: producttesting@awgc.com.au



FINAL REPORT

Internet: www.awgc.com.au

Report ID: 326452

CLAUSE 6.7 Metals

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75

mm x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts

were prepared using 1000 mL volumes of pre-conditoning water(Al 12.6).

Extraction Temperature 20°C ± 2°C.

Test Method Metals (Appendix H)

Not applicable. **Scaling Factor**

All methods used to determine concentrations of metals are based on those described in **Method of Analysis**

the US EPA method 200.8 Determination of Trace elements in Waters and Wastes by Inductively Coupled Plasma - Mass Spectrometry. The methods have been adapted for the

instrumentation in use at the Australian Water Quality Centre.

Concentration of the metals described in Table 2 of the AS/NZS 4020:2018 are determined

as follows:

Aluminium, Antimony, Arsenic, Barium, Boron, Cadmium, Chromium, Copper, Iron, Lead, Manganese, Mercury, Molybdenum, Nickel, Selenium and Silver by Inductively Coupled

Plasma Mass Spectrometry.

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
Final Extract					
Aluminium	0.001	0.032	0.034	0.035	0.2
Antimony	0.0005	<0.0005	< 0.0005	< 0.0005	0.003
Arsenic	0.0003	<0.0003	< 0.0003	< 0.0003	0.01
Barium	0.0005	0.0266	0.0265	0.0266	0.7
Boron	0.020	0.022	0.035	0.032	1.4
Cadmium	0.0001	<0.0001	<0.0001	< 0.0001	0.002
Chromium	0.0001	0.0001	0.0003	0.0003	0.05
Copper	0.0001	0.1584	0.1310	0.1341	2.0
Iron	0.0005	0.0044	0.0041	0.0042	0.3
Lead	0.0001	0.0004	0.0004	0.0005	0.01
Manganese	0.0001	0.0010	0.0010	0.0010	0.1
Mercury	0.00003	<0.00003	<0.00003	<0.00003	0.001
Molybdenum	0.0001	0.0002	0.0003	0.0002	0.05
Nickel	0.0001	0.0016	0.0016	0.0016	0.02
Selenium	0.0001	<0.0001	<0.0001	< 0.0001	0.01
Silver	0.00003	<0.00003	<0.00003	<0.00003	0.1

Evaluation The product passed the requirements of clause 6.7 when tested at an exposure of 42000 mm

² per Litre.

Number of Samples 1.

Not applicable. **Test Comment**

Dzung Bui APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025



SAW PT Final 2018.RPT

Email: producttesting@awgc.com.au



Internet: www.awqc.com.au

FINAL REPORT

Report ID: 326452

CLAUSE 6.8 Organic Compounds

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75 mm

x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts were

prepared using 1000 mL volumes of pre-conditoning water(Al 12.6).

Extraction Temperature $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

Test Method Organic Compounds (Clause 6.8). Max Allowed values are taken from the Australian Drinking

Water Guidelines and Drinking-water Standards for New Zealand. Please note, some reported

compounds have no guideline value.

Scaling Factor Not applicable.

Results

Organic Compound

Nitrosamines	Blank	Test	Max Allowed
	μg/L	μg/L	
!External Lab Report No.	ES2135439	ES2135439	
1-Nitrosopiperidine (NPip)	<0.003	<0.003	
1-Nitrosopyrrolidine (NPyr)	<0.01	<0.01	
Nitrosomorpholine (NMor)	<0.003	<0.003	
N-Nitrosodiethylamine (NDEA)	<0.01	<0.01	
N-Nitrosodimethylamine (NDMA)	<0.003	<0.003	0.1 μg/L
N-Nitrosodi-n-propylamine (NDPA)	<0.003	<0.003	
N-Nitrosomethylethylamine (NMEA)	<0.003	<0.003	

Organic Compound

Blank	Test	Max Allowed
μg/L	μg/L	
ES2135439	ES2135439	
<1.0	<1.0	
<1.0	<1.0	20 μg/L
<1.0	<1.0	200 μg/L
<1.0	<1.0	
<1.0	<1.0	
<1.0	<1.0	300 μg/L
<1.0	<1.0	
<1.0	<1.0	
<2.0	<2.0	
<1.0	<1.0	
<2.0	<2.0	9 μg/L
<1.0	<1.0	
	μg/L ES2135439 <1.0 <1.0 <1.0 <1.0 <1.0 <1.0 <1.0 <1.0	μg/L ES2135439 S2135439 S310 S310 S310 S310 S310 S310 S310 S310







Internet: www.awgc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 326452

Organic	Compound
---------	----------

Phthalate Esters	Blank	Test	Max Allowed
	μg/L	μg/L	
!External Lab Report No.	ES2135439	ES2135439	
Bis(2-ethylhexyl) phthalate	<10	<10	10 μg/L
Butyl benzyl phthalate	<2	<2	
Di(2-ethylhexyl) adipate	<2	<2	
Diethyl phthalate	<2	<2	
Dimethyl phthalate	<2	<2	
Di-n-butyl phthalate	<2	<2	
Di-n-octyl phthalate	<2	<2	

0

Organic Compound			
Polycyclic Aromatic Hydrocarbons	Blank	Test	Max Allowed
	μg/L	μg/L	
!External Lab Report No.	ES2135439	ES2135439	
Acenaphthene	<0.02	<0.02	
Acenaphthylene	<0.02	<0.02	
Anthracene	<0.02	<0.02	
Benzo(a)anthracene	<0.02	<0.02	
Benzo(a)pyrene	<0.005	<0.005	0.01 μg/L
Benzo(a)pyrene TEQ	<0.005	<0.005	
Benzo(b+j)fluoranthene	<0.02	<0.02	
Benzo(ghi)perylene	<0.02	<0.02	
Benzo(k)fluoranthene	<0.02	<0.02	
Chrysene	<0.02	<0.02	
Dibenzo(a-h)anthracene	<0.02	<0.02	
Fluoranthene	<0.02	<0.02	
Fluorene	<0.02	<0.02	
Indeno(123-cd)pyrene	<0.02	<0.02	
Naphthalene	<0.02	<0.02	
PAH - Total	<0.005	<0.005	
Phenanthrene	<0.02	<0.02	
Pyrene	<0.02	<0.02	







Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 326452

Organic Co	mpound
------------	--------

Organic Compound			
Volatile Organic Compounds GCMS	Blank	Test	Max Allowed
	μg/L	μg/L	
1 1 1 2-Tetrachloroethane	<1	<1	
1 1 1-Trichloroethane	<1	<1	
1 1 2 2-Tetrachloroethane	<1	<1	
1 1 2-Trichloroethane	<1	<1	
1 1-Dichloropropene	<1	<1	
1 2 3-Trichlorobenzene	<1	<1	
1 2 3-Trichloropropane	<1	<1	
1 2 4-Trichlorobenzene	<1	<1	
1 2 4-Trimethylbenzene	<1	<1	
1 2-Dibromo-3-chloropropane	<1	<1	1 μg/L
1 2-Dibromoethane	<1	<1	1 μg/L
1 2-Dichlorobenzene	<1	<1	1500 µg/L
1 2-Dichloroethane	<1	<1	3 μg/L
1 2-Dichloropropane	<1	<1	
1 3 5-Trimethylbenzene	<1	<1	
1 3-Dichlorobenzene	<1	<1	
1 3-Dichloropropane	<1	<1	
1 4-Dichlorobenzene	<1	<1	40 µg/L
1,1-Dichloroethane	<1	<1	
1,1-Dichloroethene	<1	<1	30 μg/L
2,2-Dichloropropane	<1	<1	
2-Chlorotoluene	<1	<1	
4-Chlorotoluene	<1	<1	
4-Isopropyltoluene	<1	<1	
Benzene	<1	<1	1 μg/L
Bromobenzene	<1	<1	
Bromochloromethane	<1	<1	
Bromodichloromethane	30	29	60 μg/L
Bromoform	6	6	100 µg/L
Bromomethane	<4	<4	
Carbon tetrachloride	<1	<1	3 μg/L
Chlorobenzene	<1	<1	300 μg/L
Chloroethane	<4	<4	
Chloroform	23	23	400 μg/L
Chloromethane	<4	<4	
cis-1 3-Dichloropropene	<1	<1	
cis-1,2-Dichloroethene	<1	<1	"
Dibromochloromethane	30	30	150 μg/L
Dibromomethane	<1	<1	
Dichlorodifluoromethane	<1	<1	
Dichloromethane	<4	<4	4 μg/L
Ethylbenzene	<1	<1	300 μg/L
Hexachlorobutadiene	<0.7	<0.7	0.7 µg/L
Isopropylbenzene	<1	<1	
m+p-Xylenes - Total	<2	<2	







Email: producttesting@awqc.com.au



Internet: www.awqc.com.au

FINAL REPORT

Report ID: 326452

Volatile Organic Compounds GCMS	Blank	Test	Max Allowed
	μg/L	μg/L	
Naphthalene	<1	<1	
n-Butylbenzene	<1	<1	
n-Propylbenzene	<1	<1	
o-Xylene	<1	<1	
sec-Butylbenzene	<1	<1	
Styrene	<1	<1	30 μg/L
tert-Butylbenzene	<1	<1	
Tetrachloroethene	<1	<1	50 μg/L
Toluene	<1	<1	800 μg/L
Total 1 2-dichloroethene	<2	<2	60 μg/L
Total 1 3-dichloropropene	<2	<2	20 μg/L
Total Trichlorobenzene	<2	<2	30 μg/L
Total Xylene	<3	<3	600 µg/L
trans-1 3-Dichloropropene	<1	<1	
trans-1,2-Dichloroethene	<1	<1	
Trichloroethene	<1	<1	
Trichlorofluoromethane	<1	<1	
Trihalomethanes - Total	89	88	250 μg/L
Vinyl chloride	<0.3	<0.3	0.3 µg/L

Evaluation The product passed the requirements of clause 6.8 when tested at an exposure of 15000 mm²

per Litre.

Number of Samples 1.

Test Comment Subcontracted testing conducted by ALS, Environmental Division, NATA accreditation no. 825

site no. 10911 and ALS Scoresby, NATA accreditation no. 992, site no. 989

Qiong Huang

APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

